

RAMAPET H1

Sales Specifications

Product: Polyethylene Terephthalate (PET) polymer for hot fill applications

Sl. No	Property	Unit	Specifications	Test Equipment
1	Intrinsic Viscosity	dl/g	0.80 ± 0.02	IR-001 (Ubbelohde Viscometer)
2	Acetaldehyde	ppm	1 Max	IR-002 (Gas Chromatograph)
3	Melting point	°C	253 ± 2.0	IR-003 (Differential Scanning Calorimeter)
4	Color b	/	-1.5 ± 1.5	IR-004 (CIE Lab)
5	Crystallinity	%	50 Min	IR-005 (Density Gradient Column)
6	Moisture content (when packed)	wt %	0.2 Max	IR-006 (Gravimetric Method)
7	Chips / gm	pieces	60 ± 5	IR-007 (Weighment Method)

Description

RAMAPET H1 has excellent optical clarity and sparkle, good thermal stability and low acetaldehyde with excellent processability (wide processing window) and high productivity. Suitable for, hot fill bottles, food containers and house hold products.

RAMAPET H1 resin is considered safe for food packaging applications based upon compliance with FDA regulation 21 CFR Section 177.1630, European Legislation EU 10/2011 and RoHS Directive 2002/95/EC and its subsequent amendments for heavy metal contents.

Warranty

Indorama warrants that its products will comply with the specifications and related regulatory compliance detailed in its publications. No other warranty, either expressed or implied regarding the suitability of the product for any particular purpose is made. The buyers are expected to make their own determination about the safety, health, environmental protection and suitability of use for their intended purpose. No warranty is made of the merchantability or fitness of any product and nothing herein waives any of the seller's conditions of sale.